

Textured HDPE Product Data Sheet

HDPE textured is a high quality high density polyethylene(HDPE) geomembrane with one or two coe extruded textured surfaces , and consisting of aproxamately 97.5% polyethylene, 2.5% carbon black and trace amounts of anti oxidents and heat stabilizers; no other additives, fillers or extenders are used. The resin used is specially formulated, virgin polyethylene and is designed specifically for flexible geomembrane applications. HDPE textured has excellent resistance to UV radiation and is suitable for exposed conditions. This product allows projects with greater slopes to be designed since frictional characteristics are enhanced. Provides safer working surface for sub zero temperature installations. These product specifications meet or exceed GRI GM13

TESTED PROPERTY	TEST METHOD	FREQUENCY	MINIMUM VALUE			
			HDT	HDT	HDT	HDT
Product Code			040A000	060A000	080A000	100A000
Avg.Thickness, mils (mm)	ASTM D5994	Every roll	36 (0.91)	54 (1.4)	72 (1.8)	90 (2.3)
Density, g/cm3	ASTM D1505	2000,000lb	0.94	0.94	0.94	0.94
Tensile Properties (each direction)		20,000lb				
Strength at Break N/mm (lb/in-width)	ASTM D6693,Type IV Dumbell, 2 ipm G.L.=2.0in (51mm) G.L. 1.3in (33mm)		11 (60)	16 (90)	21 (120)	27 (150)
Stentgh at Yield, N/mm (lb/in-width)			15 (84)	23 (130)	30 (173)	38 (216)
Elongation at Break, %			150	150	150	150
Elongation at Yield, %			13	13	13	13
Tear resistance, N (lb),	ASTM D1004	45,000lb	125 (28)	187 (42)	249 (56)	311 (70)
Puncture Resistance, N (lb)	ASTMD 4833	45,000lb	320 (72)	480 (108)	641 (144)	801 (180)
Carbon Black Content, %	ASTMD 1603	20,000lb	2.0	2.0	2.0	2.0
Notched Tensile Load2, hrs	ASTMD 5397,Appendix	2000,000lb	400	400	400	400
Low Temperature Brittleness	ASTM D 746	< -77 degress Celcius				
Roll Length, m			215	129	98.5	77
Roll Width, m			6.9	6.9	6.9	6.9
Roll Area, m2			1484	893	680	531
HDPE comes in both black single and double textured and white reflective single and double textured.						

Note:

This information is for referance purposes only, A&A Technical Services(A&A) assumes no liability in connection with the use of the information. Please contact A&A for current standard minimum quality assurance procedures and specifications.